STAT



STAT

SOVIET RARE METALS STANDARDS, USES, ALLOCATIONS

Redkiye Metally Moscow, 1951

O. A. Songina

[Comment: The following was taken from the book Redkije Metally, by O. A. Songina, published by Metallurgizdat, Moscow, 1951.]

Tungsten

Γ

About 90 percent of all Soviet tungsten output (ore concentrate) is used in the production of ferrotungsten.

Approximately 2 percent of all tungsten output is used in the production of stellites. The usual composition range of these stellites is as follows: 3-15 percent W, 25-35 percent Cr, 45-65 percent Co, 0.5-2.7 percent C.

Tungsten salts are used to fireproof some fabrics. Heavy, expensive silks owe their beauty to the tungsten salts with which they are permeated.

Pure tyngsten is used in chemical analyses. Tungsten compounds are used as catalysts.

Molybdenum

The steel industry uses about 90 percent of all USSR molybdenum output. Molybdenum is introduced into steel either in the form of ferromolybdenum, with about an 80 percent molybdenum content, or in the form of calcium molybdate. The latter is currently regarded as preferable.

Rhenium

Rhenium has not yet found extensive application in the USSR.

Tantalum

Lately, tantalum has been used in pipes used in the manufacture of hydrochloric acid. The high initial cost of such pipelines is compensated for by their virtually unlimited length of service.

Tantalum is used in super-hard alloys because of its ability to form the hard carbide ${\tt TiC}$.

Columbium

Ferrocolumbium, with up to 60 percent columbium, is used to introduce columbium into steel. Ferrocolumbium is produced either by the direct smelting of concentrates in an electric furnace or by the aluminothermic method.

STAT

- 1 -

Sanitized Copy	Approve	d for Rele	ease 2011	/09/14 :	CIA-RDP80	-00809A00	0700190099-1

Titenium

Γ

Armor plate is strengthened when "titanized," i.e., when the plate is coated with titanium powder and heated in an atmosphere of hydrogen, thus diffusing the titanium into the steel case.

<u>Gallium</u>

Gallium is not toxic and is therefore used in dental fillings (50 percent Sn, 34 percent Bi, 15 percent Cd, 1 percent Ga).

Indium

Indium is rather widely used. Automotive and aircraft engine silver-cadmium and copper-lead bearings are plated with indium.

Thallium

Thallium is used in some lead (20-65 percent T1), and silver (10-22 percent T1) corrosion-resistant alloys. It is also used in electrodes for copper electrolysis (70 percent Pb, 20 percent Sn, 10 percent T1) and in some bearing alloys (72 percent Pb, 8 percent T1, 15 percent Sb, 5 percent Sn).

STAT



- 2 -

STAT

Sanitized Copy Approved for Release 2011/09/14 : CIA-RDP80-00809A000700190099-1

Tungsten Concentrates (GOST 213-49)

				Cl	nemical (Composition	on in Per	cent	: · · · · ·	
i .	Tungsten Anhydride	Manganese	Silicon	Phos-						
Grade	(minimum)	0xide	Dioxide	phorus	Sulfur	Arsenic	Tin	Copper	Mclybdenum	<u>.</u>
KVGl	63	18	5	0.03	0.6	0.10	0.10	0.18	1) odenom	<u>Uses</u> Ferrotungsten V1
KVG2	60	18	5	0.04	0.8	0.10	0.15	0.22		
KVG3	60	18	5	0.05	0.8	0.20	0.20	0.22		Ferrotungsten V2 Ferrotungsten V3
KShl	55	4	10	0.04	0.6	0.05	0.08	0.17		
KSh2	50	4	10	0.08	0.8	0.08	0.15	0.19		Ferrotungsten Vl
KSh3	50	4	10	0.11	0.8	0.20	0.20	0.20		Ferrotungsten V2
KMSh1	65	0.10	1.5	0.04	0.3	0:04	0.05	0.10	0.1	Ferrotungeten V3
KMSh2	60	0.10	3.0	0.08	0.5	- 0.05	0.05	0.10	2-4.5	Ferrotungster Vla
KVGA	60		5	0.2	3	-	•	0.10	2-4.5	Ferrotungsten V2a
KVGK	60				_	0.1	1.5		0.06	Tungsten anhydride
KShA1	50		5	0.1	3	0.1	1.5		0.01	Tungstic scid
KShA2	•				3	0.1	1.5		0.05	Tungsten anhydride
	40			0.2	3	0.1	1.5			Tungsten anhydride
KShA3	40				3	0.1	1.5		0.25	Tungster anhydride

STAT

STAT

000700190099 1

Sanitized Copy Approved for Release 2011/09/14 : CIA-RDP80-00809A000700190099-1

Sanitized Copy Approved for Release 2011/09/14 : CIA-RDP80-00809A000700190099-1

STAT

Average Composition of Molybdenite and Technical Specifications for Molbdenum Concentrate (GOST 212-48) (In percent)

Molybdenite	Мо	Pb	<u>Cu</u>	<u>Zn</u>	<u>Fe</u>	As	CaO	MgO	MnO	A1203	\$102	. <u>P</u>	Sn	Was a
Veiny	0.42	0.015			3.07	Traces	3.5	1.07				-	<u>511</u>	<u>Uses</u>
Skarny	0.48		0.02	0.03	9.36	0.07	17.33					termined		
Concentrate										•	,			
кмі	50		0.5			0.07					_			
KM2	48										5	0.07	0.07	Ferromolybdenum Mol
	40		1.0			0.07					7	0.07	0.07	Ferromolybdenum Mol
кмз	47		2.0			0.07								refromorybdenum Mol
						0.01					9	0.15	0.07	Ferromclybdenum Mo2, Mo3, calcium molybdate

- E N D -

STAT



Sanitized Copy Approved for Release 2011/09/14 : CIA-RDP80-00809A000700190099-1